

检测报告 Test Report



报告编号 A2190243009101002E

第 1 页共 5 页

Report No. A2190243009101002E

Page 1 of 5

申请单位 沈阳仁辉消防科技有限公司

Applicant Shenyang Renhui Fire Technology Co., Ltd.

地址 沈阳市于洪区永康街 2-2 号

Address 2-2 Yongkang Street, Yuhong Hardware Industrial Park, Yuhong District, Shenyang

以下测试之样品及样品信息由申请者提供并确认

The following sample(s) and sample information was/were submitted and identified by/on the behalf of the client

样品名称	无涂层灭火器碳钢筒体
Sample Name	Uncoated carbon steel fire extinguisher cylinder
材质 Material	碳钢 carbon steel
样品接收状态	正常
Sample Receiving State	Normal
样品接收日期	2019.09.16
Sample Received Date	Sep. 16, 2019
样品检测日期	2019.09.16-2019.09.25
Testing Period	Sep. 16, 2019-Sep. 25, 2019

检测要求 Test Requested

序号 No.	测试项目 Test Item
1	腐蚀试验 Corrosion test

检测结果 Test Result(s): 请参见后续页面 Please see the following pages.

批准
Approved by

李海峰

日期
Date

2019.09.25
Sep. 25, 2019

李海峰
授权签字人
Approved Signatory
华测检测认证集团有限公司
Centre Testing International Group
Beijing CO., LTD.



No.R01C185DCB
北京市北京经济技术开发区科创十四街 99 号 21 幢
Building 21, No.99, Kechuang Fourteen Street,
Beijing Economic-Technological Development Area,
Beijing, China;

检测报告 Test Report

报告编号 A2190243009101002E

第 2 页共 5 页

Report No. A2190243009101002E

Page 2 of 5

测试样品

Tested Sample(s)

样品编号 Sample No.	样品名称 Sample Name	材质 Material	样品数量 Quantity
A2190243009101002	无涂层灭火器碳钢筒体 Uncoated carbon steel fire extinguisher cylinder	碳钢 carbon steel	1pc

样品图片

Sample Photo(s)



A2190243009101002

检测报告 Test Report

报告编号 A2190243009101002E

第 3 页共 5 页

Report No. A2190243009101002E

Page 3 of 5

测试项目：腐蚀试验

Test Item: Corrosion test

1. 测试设备 Test Equipment

设备名称 Equipment Name	型号 Model
气流式盐雾腐蚀试验箱 Air flow salt spray corrosion test box	NQ-0750

2. 环境条件 Environmental Conditions

温度：22℃±5℃ 湿度：30~50%RH

3. 测试标准 Test Standard: 依客户要求 According to the customer's requirements

4. 测试条件

Test Condition

试验箱温度：35℃

饱和器温度：47℃

溶液：水系灭火剂(S-3-AB-IP)

测试时间：96 小时

备注：试验箱温度和饱和器温度条件参考标准 GB/T 10125-2012。溶液为客户提供。

样品四周的切割边缘不参与评价。

Temperature of the chamber: 35℃

Temperature of the saturation tower: 47℃

Solution: Water system extinguishing agent (S-3-AB-IP)

Test duration: 96hours

Remarks: Test chamber temperature and saturator temperature conditions reference standard GB/T 10125-2012. Solution for customers. The cutting edges around the sample did not participate in the evaluation.

检测报告 Test Report

报告编号 A2190243009101002E

第 4 页共 5 页

Report No. A2190243009101002E

Page 4 of 5


5. 测试结果

Test Result(s)

样品编号 Sample No.	判定依据 Judgment Basis	测试结果（目视检查） Test Results (Visual Inspection)
A2190243009101002	样品表面是否有变化 Whether the surface of the sample changes	样品表面无变化 No change in sample surface
备注：判定依据由客户提供。 Note: the decision basis is provided by the customer.		


测试图片

Test Photo(s)



测试后样品图片

Sample Photo(s) after the test



A2190243009101002

检测报告 Test Report

报告编号 A2190243009101002E

第 5 页共 5 页

Report No. A2190243009101002E

Page 5 of 5

备注：本报告中的数据结果供科研、教学、企业内部质量控制、企业产品研发等目的用。

Remark: The testing data and result(s) in this report is(are) just for scientific research, education, internal quality control and product development etc.

*** 报告结束 ***

*** End of Report ***

声明：

Statement:

1. 检测报告无批准人签字、“专用章”及报告骑缝章无效；

This report is considered invalid without approved signature, special seal and the seal on the perforation;

2. 样品及样品信息由申请者提供，申请者应对其真实性负责，CTI 未核实其真实性；

The sample(s) and sample information was/were provided by the client who should be responsible for the authenticity which CTI hasn't verified;

3. 本报告检测结果仅对受测样品负责；

The result(s) shown in this report refer(s) only to the sample(s) tested;

4. 未经 CTI 书面同意，不得部分复制本报告。

Without written approval of CTI, this report can't be reproduced except in full;

5. 如检测报告中的英文内容与中文内容有差异，以中文为准。

In case of any discrepancy between the English version and Chinese version of the testing reports(if generated), the Chinese version shall prevail.